

Pre-Painted Sheet
AS2000
AS1500
AS1000

AS2000, AS1500, AS1000 Technical Data Sheet

Technical Engineering Properties

AS2000, AS1500, and AS1000 coil coated aluminum sheet is offered in 0.080", 0.059", and 0.039" thickness.

U.S. and Metric Equivalent

PROPERTY	Units	AS2000 0.080" Aluminum Sheet	AS1500 0.059" Aluminum Sheet	AS1000 0.039" Aluminum Sheet
THICKNESS	in mm	0.08 2.0	0.059 1.5	0.039 1.0
THICKNESS TOLERANCE	in mm	+/-0.003 +/-0.08	+/-0.003 +/-0.07	+/-0.002 +/-0.05
AVAILABLE WIDTH	in mm	62, 59, 51, 39 1575, 1499, 1295, 991	62, 59, 51, 39 1575, 1499, 1295, 991	62, 59, 51, 39 1575, 1499, 1295, 991
WIDTH TOLERANCE	in mm	-0/+0.12 -0/+3	+/-0.12 +/-3	-0/+0.12 -0/+3
MAX. LENGTH	in mm	157.5 4000	157.5 4000	120 3084
LENGTH TOLERANCE	in	-0, +0.25	-0, +0.25	-0, +0.25
WEIGHT	lb/ft ² kg/m ²	1.13 5.52	0.83 4.05	0.52 2.78
ALLOYS (AI) AND TEMPER	N/A	3005 H42	3005 H42	3005 H44
ALLOWABLE BENDING STRESS	lb/in ² MPa	11,500 79.3	11,500 79.3	11,500 79.3
COEFF. OF EXPANSION	in/in/°F mm/mm/°C	1.16x10 ⁻⁵ 2.1x10 ⁻⁵	1.16x10 ⁻⁵ 2.1x10 ⁻⁵	1.16x10 ⁻⁵ 2.1x10 ⁻⁵
STIFFNESS (EI) ASTM C393	lbf/in ² /in MPa-cm ² /m	431.3 118.15	172.7 49.35	49.9 14.59
FLEXURAL MODULUS ASTM C393 (E)	lbf/in ² MPa	1.01x10 ⁷ 6.95x10 ⁴	1.01x10 ⁷ 6.95x10 ⁴	1.01x10 ⁷ 6.95x10 ⁴
FINISHES / PERFORMANCE	N/A	Coil Coated Pretreatment with 2 or 3-coat Meets AAMA 2605 / 2604 / 2603	Coil Coated Pretreatment with 2 or 3-coat Meets AAMA 2605 / 2604 / 2603	Coil Coated Pretreatment with 2 or 3-coat Meets AAMA 2605 / 2604 / 2603

Information contained herein or related hereto is intended only for evaluation by technically skilled persons, with any use thereof to be at their independent discretion and risk. Such information is believed to be reliable, but AAP shall have no responsibility or liability for results obtained or damages resulting from such use. AAP grants no license under, and shall have no responsibility or liability for infringement of, any patent or other proprietary right. Nothing in this document should be construed as a warranty or guarantee by AAP, and the only applicable warranties will be those set forth in AAP's acknowledgment or in any printed warranty documents issued by AAP. The foregoing may be waived or modified only in writing by an AAP officer.

Disclaimer:

Laws and building and safety codes governing the design and use of AAP's products, and specifically aluminum composite materials, vary widely. It is the responsibility of the owner, the architect, the general contractor, the installer and the fabricator/transformer, consistent with their roles, to determine the appropriate materials for a project in strict conformity to all applicable national, regional and local building codes and regulations. REYNOBOND® FR AND AS3000B HAVE SUCCESSFULLY PASSED US NFPA 285, E84 AND CANADA S134, S102 TESTS AS A PART OF AN ASSEMBLY. ENSURE THE PRODUCT IS USED IN A SYSTEM THAT COMPLIES WITH ALL APPLICABLE REGULATIONS. REYNOBOND® PE IS COMBUSTIBLE; IT COULD CATCH FIRE AND BURN. ANY LABORATORY TESTING INFORMATION PROVIDED BY AAP LLC APPLIES ONLY TO THE PARTICULAR PRODUCT OR ASSEMBLY TESTED AND DOES NOT NECESSARILY REPRESENT HOW PRODUCTS WILL ACTUALLY PERFORM IN USE. REPORTS AND TEST DATA CORRESPONDING TO A PARTICULAR TESTED PRODUCT SAMPLE OR ASSEMBLY ARE NOT A GUARANTEE THAT THE SAME PRODUCT OR ASSEMBLY WOULD ALWAYS ACHIEVE THE SAME TEST RESULT.

Slight variations in color, gloss and texture can occur between different paint production batches. Paint variations within a specific color, especially for mica and metallic colors, can and do occur that are visible to the human eye, but are within industry tolerances.

ARCONIC ARCHITECTURAL PRODUCTS LLC

50 Industrial Boulevard
Eastman, GA 31023-4129
Tel. 800 841 7774
arconicarchitecturalproducts.com
EC 99603-008

